



Martini dECO QUIET BOARD

High performance acoustic with no fabric

A large, light blue, stylized lowercase letter 'm' graphic that spans across the bottom of the page.

CSR

dECO Quiet Board

- High performance sound absorptive acoustic board to control reverberate noise.
- Durable and resilient semi-ridge surface.
- Lightweight and easy to handle boards make installation quick and simple.
- Direct fixed with exposed edges or framed with aluminium trimming for large wall spaces or feature areas.
- For maximum design flexibility, boards can be precision cut to size.
- Self-healing pinable surface for use in collaborative work and educational spaces.
- Available in black and white.

Applications

Cover grade substrate for interior wall and ceiling panelling, workstation partitions and pinboards in spaces such as offices, meeting rooms, theatres, restaurants, libraries, classrooms, sports halls and auditoriums.

Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 80% recycled fibre content from post-consumer PET packaging such as empty drink bottles.

- GreenTag^{Cert™} certified
- Environmental Product Declaration (EPD) Certified in accordance with ISO 14025
- Product Health Declaration (PHD) certified
- Declare certified
- Suitable for Green Star[™] projects
- No red list chemicals are present
- No ozone-depleting gases are used during the manufacturing process
- Volatile organic compounds (VOCs) generated in the manufacturing process is classified as low (0.01 mg/m³)s
- Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- High reuse potential



Martini's Product Stewardship Program can be viewed at www.csrmartini.com.au

Acoustic Performance

Frequencies	125hz	250hz	500hz	1,000hz	2,000hz	4,000hz	NRC
25mm (direct fix)	0.10	0.45	0.80	0.95	0.95	0.90	0.85
50mm (direct fix)	0.35	0.80	1.00	1.00	1.00	1.00	1.00
75mm (direct fix)	0.65	1.00	1.00	1.00	1.00	1.00	1.00
100mm (direct fix)	0.80	1.00	1.00	1.00	1.00	1.00	0.90

Tested in accordance with AS/ISO 354:2006.

Product Specifications

Thickness (mm)	25	25	50	50	75	75	100	100
Length (mm)	2420	2720	2420	2720	2420	2720	2420	2720
Width (mm)	1210	1210	1210	1210	1210	1210	1210	1210
Coverage (m ²)	2.92	3.29	2.92	3.29	2.92	3.29	2.92	3.29
Sheets per box	6	6	3	3	2	2	1	1
R-value	0.68*	0.68*	1.36	1.36	2.2	2.2	3	3

Tolerance in sizes: thickness +/- 2mm; length +/- 10mm; width +/- 5mm

* Derived calculation

Physical description and properties

Melting point:	250°C
Flash point:	None allocated
Other properties:	Non-allergenic, low irritant, low flame response, resilient
Ingredients:	Organic, long chain synthetic polymer
Max service temp:	110°C
Alkalinity:	pH 7.8 (pH 7 is neutral)
Moisture absorption:	Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume

25mm, 50mm, 75mm
Tested to AS ISO 9705 Corner
Burn in accordance with AS 5637.1

Group 1
SMOGRA not
more than
 $100\text{m}^2/\text{s}^2 \times 1000$

100mm
Tested to AS ISO 9705 Corner Burn
in accordance with AS 5637.1

Group 2
SMOGRA not
more than
 $100\text{m}^2/\text{s}^2 \times 1000$

Fire resistance:

The following results were obtained when CSR Martini dECO Quiet Board was subjected to early fire hazard testing in accordance with Australian Standards AS 1530.3

Ignitability	0
Spread of Flame	0
Heat Evolved	0
Smoke Developed	0-1

csrmartini.com.au

CSR Martini Pty Limited
P.O. Box 560, Ingleburn NSW 1890
martinienquiries@csr.com.au
1300 767 776

04/19



Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.