



Martini ABSORB

High performance sound absorptive insulation

A large, light blue, stylized lowercase letter 'm' graphic that spans across the bottom of the page.

CSR

Martini Absorb

- Thermally-bonded polyester fibre insulation specifically designed to provide high performance sound absorption across a range of frequencies to reduce echo and reverberation.
- Made in a range of densities and thicknesses with fibre blends specifically engineered to provide maximum thermal and acoustic performance in many diverse commercial, residential, community and industrial applications.
- Non-irritant and does not require any protective clothing or masks during installation.
- Available in standard white and black colour. Grey available upon request.

Applications

Martini Absorb is ideal for use behind perforated panelling and ceilings in sports halls, cinemas, studios, industrial enclosures, HVAC ducts, silencers or plant rooms.

Martini Absorb can also be laid above suspended ceilings. Absorb is not suitable for fully exposed applications or where a decorative finish is required.

Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 80% recycled fibre content from post-consumer PET packaging such as empty drink bottles.

- GreenTag^{Cert}™ certified
- Environmental Product Declaration (EPD) Certified in accordance with ISO 14025
- Product Health Declaration (PHD) certified
- Declare certified
- Suitable for Green Star™ projects
- No red list chemicals are present
- No ozone-depleting gases are used during the manufacturing process
- Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- High reuse potential



Martini's Product Stewardship Program can be viewed at www.csrmartini.com.au

Acoustic Performance

Frequencies	125hz	250hz	500hz	1,000hz	2,000hz	4,000hz	Alpha W	NRC
MD 25	0.14	0.33	0.59	0.79	0.84	0.89	0.60	0.65
MD 50	0.24	0.54	0.90	0.98	1.01	1.06	0.85	0.85
HD 25	0.12	0.29	0.62	0.78	0.91	0.92	0.60	0.65
HD 50	0.22	0.54	1.02	1.07	1.04	1.11	0.90	0.95
HD 75	0.41	0.85	1.15	1.11	1.07	1.16	1.00	1.05
HD 100	0.54	1.12	1.13	0.97	0.94	0.99	1.00	1.00
XHD 25*	0.15	0.35	0.60	0.80	0.85	0.95	0.70	0.70
XHD 50	0.19	0.62	1.01	1.02	0.98	0.96	0.90	0.90
XHD 75*	0.45	0.80	1.00	1.00	1.00	1.00	1.00	1.00
XHD 100	0.60	1.18	1.15	0.99	1.00	1.01	1.00	1.10
XXHD 30	0.11	0.42	0.76	0.89	0.86	0.88	0.70	0.70
XXHD 50	0.25	0.65	0.95	0.95	0.95	0.95	0.95	0.90
XXHD 75	0.40	0.87	0.96	0.95	0.87	0.89	1.00	0.95

Tested in accordance with AS/ISO 354:2006. *Opinion derived from empirical data.

Flow Resistivity

Product	Absorb HD	Absorb XHD	Absorb XXHD
MKS RAYL/M	7,994	14,693	21,008

Tested in accordance with ASTM C 522-03

Product Specifications

Product	Thickness (mm)	Length (mm)	Width (mm)	Sheets /pack	m ² /pack
MD 25	25	2400	1200	12	34.56
MD 50	50	2400	1200	6	17.28
MD 75	75	2400	1200	4	11.52
MD 100	100	2400	1200	3	8.64
HD 25	25	2400	1200	12	34.56
HD 50	50	2400	1200	6	17.28
HD 75	75	2400	1200	4	11.52
HD 100	100	2400	1200	3	8.64
XHD 25	25	2400	1200	10	28.80
XHD 50	50	2400	1200	6	17.28
XHD 75	75	2400	1200	4	11.52
XHD 100	100	2400	1200	3	8.6
XXHD 30	30	2400	1200	10	28.8
XXHD 50	50	2400	1200	3	8.64
XXHD 75	75	2400	1200	2	5.76
XXHD 100	100	2400	1200	2	5.76

Absorb LD 75 and 100 is also available as an un-rated low density product

Martini Absorb

Physical Description and Properties

Flash point:	None allocated	
Other properties:	Non-allergenic, low irritant, low flame response, resilient	
Ingredients:	Organic, long chain synthetic polymer	
Max service temp:	150°C	
Alkalinity:	pH 7.8 (pH 7 is neutral)	
Moisture absorption:	Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume	
Fire resistance:	<p>Tested to AS ISO 9705 Corner Burn in accordance with AS 5637.1</p> <p>Variations up to XXHD 75mm Group 1-S SMOGRA not more than 100m²/s² x 1000</p> <p>XXHD 100mm Group 2-S SMOGRA not more than 100m²/s² x 1000</p> <p>Early fire hazard testing in accordance with AS 1530.3. Variations of Martini Absorb XHD 75 and higher achieve</p>	<p>Ignitability 0</p> <p>Spread of Flame 0</p> <p>Heat Evolved 0</p> <p>Smoke Developed 2</p>
	Variations of Martini Absorb XHD 50 and below achieve	<p>Ignitability 10</p> <p>Spread of Flame 0</p> <p>Heat Evolved 1</p> <p>Smoke Developed 3</p>

csrmartini.com.au

CSR Martini Pty Limited
P.O. Box 560, Ingleburn NSW 1890
martinienquiries@csr.com.au
1300 767 776

04/21



Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.