

Martini dECO FLEX

Velcro® receptive, flexible acoustic wall covering







dECO Flex 10 - 12mm

- Flexible wall finish for straight and curved walls.
- Narrow range frequency absorption to reduce reverberated noise.
- Velcro® receptive surface.

Applications

Used in high schools, primary schools and child care centres to help children learn and in offices and public spaces such as libraries to facilitate communication and the exchange of ideas.

Decorative Finishes

dECO Velour is available in an extensive colour palette. dECO Velour is a non-woven fabric with nap and no pattern repeat.

Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 80% recycled fibre content from post-consumer PET packaging such as empty drink bottles.

- GreenTag^{CertTM} certified
- Environmental Product Declaration (EPD)
 Certified in accordance with ISO 14025
- Product Health Declaration (PHD) certified
- · Declare certified
- Suitable for Green Star™ projects
- · No red list chemicals are present
- No ozone-depleting gases are used during the manufacturing process
- · Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- · High reuse potential






Martini's Product Stewardship Program can be viewed at www.csrmartini.com.au

Martini dECO FLEX 2

Finishes





Acoustic Performance

Frequencies	125hz	250hz	500hz	1,000hz	2,000hz	4,000hz	NRC
Direct Fix	0.05	0.10	0.30	0.50	0.75	0.95	0.40

Tested in accordance with AS/ISO 354:2006

Product Specifications

Product	Thickness (mm)	Width (m)	Roll Length (m)*
dECO Flex	10-12	1220	25

Tolerance in sizes: thickness +/- 2mm; width +/- 5mm.

^{*}Please note that due to the nature of the manufacturing process, there is a 10% over or under supply. Other roll lengths available upon request. Minimum length 7m.



Physical Description and Properties

Melting point: 250°C

Flash point: None allocated

Other properties: Non-allergenic, low irritant, low flame response, resilient

Ingredients: Organic, long chain synthetic polymer

Max service temp: 110° C

Alkalinity: pH 7.8 (pH 7 is neutral)

Moisture absorption: Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture

absorption of less than 0.2% by volume

Fire resistance: Tested to AS ISO 9705 Corner Burn

in accordance with AS 5637.1

SMOGRA not more than $100\text{m}^2/\text{s}^2 \times 1000$

Group 1

Martini dECO FLEX 5

csrmartini.com.au

CSR Martini Pty Limited P.O. Box 560, Ingleburn NSW 1890 martinienquiries@csr.com.au 1300 767 776

04/21











Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.