



# Martini dECO DELUXE

---

High density acoustic board

---



## dECO Deluxe

- High end ceiling or wall finish.
- Sound absorptive board across a range of frequencies.
- Board for fabric wrapping.
- Direct fix installation.

## Applications

Rigid board for interior wall and ceiling panelling, workstation partitions and pinboards in spaces such as offices, meeting rooms, theatres, restaurants, libraries, classrooms, sports halls and auditoriums.

## Decorative Finishes

dECO Deluxe can be fabric faced or fabric wrapped to complement any interior and can be used as a functional decorative feature wall. For other finishing options, consult your CSR Martini representative.

## Installation

For product installation instructions, please refer to the CSR Martini installation guide available at [csrmartini.com.au](http://csrmartini.com.au)

## Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 0-60% recycled fibre content from post-consumer, pre-consumer and post-industrial PET.

- Global GreenTag certified GreenRate
- Environmental Product Declaration (EPD) Certified in accordance with ISO 14025
- Global GreenTag HealthRate
- Declare Transparency Label
- Suitable for Green Star™ projects
- LBC Red List Free
- No ozone-depleting gases are used during the manufacturing process
- Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- High reuse potential



Martini's Product Stewardship Program can be viewed at [www.csrmartini.com.au](http://www.csrmartini.com.au)

## Colours



White



Black

## Acoustic Performance

Frequencies	125hz	250hz	500hz	1,000hz	2,000hz	4,000hz	NRC
<b>24mm</b>	0.05	0.20	0.55	0.85	0.95	0.95	<b>0.65</b>

Tested in accordance with AS/ISO 354:2006.

## Product Specifications

Product	Thickness (mm)	Length (mm)	Width (mm)	Coverage /Panel m <sup>2</sup>	Boards /pack*
<b>dECO Deluxe White</b>	24	2410	1210	2.92	4
<b>dECO Deluxe Black</b>	24	2410	1210	2.92	4

Tolerance in sizes: thickness +/- 2mm; length +/- 10mm; width +/- 5mm

\*Product is sold per unit, reference to pack size for delivery/packing purposes only

## Physical Description and Properties

**Melting point:** 250°C

**Flash point:** None allocated

**Other properties:** Non-allergenic, low irritant, low flame response, resilient

**Ingredients:** Organic, long chain synthetic polymer

**Max service temp:** 110°C

**Alkalinity:** pH 7.8 (pH 7 is neutral)

**Moisture absorption:** Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume

**Fire resistance:** Tested to AS ISO 9705 Corner Burn  
in accordance with AS 5637.1

**Group 1**  
SMOGRA not  
more than  
100m<sup>2</sup>/s<sup>2</sup> x 1000

Proudly distributed by



# csrmartini.com.au

CSR Martini Pty Limited  
P.O. Box 560, Ingleburn NSW 1890  
[martinienquiries@csr.com.au](mailto:martinienquiries@csr.com.au)  
1300 767 776

---

12/25



Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.